

(www.qindutech.com Q)



## **Basic Parameters**


Dimension:100\*60\*25 mm Weight: 74g(with battery)

Power: 2 AAA batteries Operating Temperature: -20°C~50°C

Storage Temperature:-20°C~60°C Material: ABS

Measuring principles: Fe: magnetic induction;

NFE: eddy current effect; Probe Tip: ruby



## P-200 Coating Thickness Guages

The instrument utilizes imported sensors and microcontroller technology, integrating magnetic induction technology, eddy current technology, and precision compensation algorithms. It features a dual-function built-in probe that automatically identifies ferrous or non-ferrous substrate materials. The gauge is characterized by its small measurement error, high reliability, good stability, and ease of operation, making it an essential tool for controlling and ensuring product quality. It is widely used in inspection fields such as automotive testing, manufacturing, metal processing, chemical industry, and commercial inspection. The gauge can non-destructively measure the thickness of non-magnetic coatings (such as aluminum, chrome, copper, enamel, rubber, paint, etc.) on magnetic metal substrates (such as steel, iron, alloys, and hard magnetic steel) as well as the thickness of non-conductive coatings (such as enamel, rubber, paint, plastic, etc.) on non-magnetic conductive substrates (such as copper, aluminum, zinc, tin, etc.).





Iron-Aluminum-Zinc





Iron Galvanizing






elligent Wi

Wide Measuremen Range: 3500 µm

## **Product Features**

**Putty Testing** 





Made from ultra-hard ruby material, highly wear-resistant, and offers a longer service life.



Abnormal Alarm

Red lights indicate upper and lower limits. Yellow light indicates material abnormalities.



□ Screen Inversion Display

Automatically inverts 180°, making it convenient to view data.

## **Technical Index**

Measuring Range: 0 to 3500 µm Min Measuring Dimension: 15 x 15 mm

Measuring Accuracy: ±(1+2%\*H)µm

Units: µm/mil

Resolution: 0.1 μm (1-100 μm); 1 μm (100-3500 μm) Measuring Time: 0.4 seconds

Min Curvature: Convexity 5mm/0.2inch; concave 25mm /1inch

Min Substrate Thickness: Ferrous (FE): 0.2 mm/Non-ferrous (NFE): 0.1 mm



**&** 189-0382-4651

High-tech Development Zone, Zhengzhou City, China